



Test method in accordance to ISO 354

Isolamin PADEC16P
Perforation ration 24%

100 k	0,09	α
125 k	0,12	α
160 k	0,12	α
200 k	0,16	α
250 k	0,25	α
315 k	0,31	α
400 k	0,45	α
500 k	0,58	α
630 k	0,73	α
800 k	0,83	α
1 k	0,85	α
1,25 k	0,87	α
1,6 k	0,87	α
2 k	0,90	α
2,5 k	0,91	α
3,15 k	0,82	α